

TECHNICAL SHEET



Article:	B0510 ARGO
Norm:	EN ISO 20345:2011
Safety Class:	S2 SRC
Footwear height:	Mod. B, H 113 mm (≥ 113 mm; Rif. EN ISO 20345-5.2.2)
Width:	11
Construction:	STROBEL; MONO-DENSITY PU -
Cleaning and maintenance:	Use only soft brushes and water. Do not use substances like alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.
Suggested fields:	Food industry, chemical-pharmaceutical industry.

Entire footwear: components					
Component	Description	Value	Norm requirements	EN 20345	
Steel toe-cap	Impact resistance(200 J)				
	• Free height after impact	14 mm	≥ 14 mm	5.3.2.3	
	Compression resistance (15 kN)				
	• Free height after compression	14,5 mm	≥ 14 mm	5.3.2.4	
Sole (SRC)	Slip resistance				
	• SRA – Sole (entire sole)	0,38	$\geq 0,32$	5.3.5.4	
	• SRA – Heel (Angle of 7°)	0,35	$\geq 0,28$	5.3.5.4	
	• SRB – Sole (entire sole)	0,18	$\geq 0,18$	5.3.5.4	
	• SRB – Heel (Angle of 7°)	0,13	$\geq 0,13$	5.3.5.4	
(P)	Puncture resistance	N/A	≥ 1100 N	6.2.1.1.2	
Footbed (A)	Antistatic properties				
	• Electrical resistance	Dry: $10,0 \times 10^8 \Omega$ Humid: $9,29 \times 10^8 \Omega$	$\geq 10^5 \Omega$, $\leq 10^9 \Omega$ $\geq 10^5 \Omega$, $\leq 10^9 \Omega$	6.2.2.2 6.2.2.2	
Sole/Upper	Thermal insulation				
	Heat (HI)	Insole temperature increase	N/A	$\leq 22^\circ\text{C}$	6.2.3.1
	Cold (CI)	Insole temperature decrease	N/A	$\leq 10^\circ\text{C}$	6.2.3.2
Heel (E)	Shock-absorption in the heel region	32 J	≥ 20 J	6.2.4	
(WR)	Water resistance (Water absorption)	N/A	≤ 3 cm ²	6.2.5	
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6	

Upper				
Component	Description	Value	Norm requirements	EN 20345
Microfibre	Tear resistance	90 N	≥ 60 N	5.4.3
	Traction resistance	N/A	≥ 15 N/mm ²	5.4.4
	Water steam permeability	1,5 mg/cm ² h	$\geq 0,8$ mg/cm ² h	5.4.6
	pH value	N/A	$\geq 3,2$	5.4.7
	Chromium VI	Not detected	Not detectable	5.4.9
	Water passed	0,2 g	$\leq 0,2$ g	6.3
	Water absorption	22 %	$\leq 30\%$	6.3

Lining				
Component	Description	Value	Norm requirements	EN 20345
3D hi-tech fabric	Tear resistance	30 N	≥ 15 N	5.5.1
	Abrasion resistance	<ul style="list-style-type: none"> Dry: the surface shows no holes Humid: the surface shows no holes 	No holes till 51.200 cycles	5.5.2
	Water steam permeability	7,2 mg/cm ² h	≥ 2,0 mg/cm ² h	5.5.3
	pH value	N/A	Not detectable	5.5.4
	Chromium VI	N/A	Not detectable	5.5.5

Insole				
Component	Description	Value	Norm requirements	EN 20345
TNT	Thickness	2 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	92mg/cm ²	≥ 70 mg/cm ²	5.7.3
	Water release	90%	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤to norms reference	5.7.4.1
	Chromium VI	N/A	Not detectable	5.7.5

Removable footbed				
Component	Description	Value	Norm requirements	EN 20345
Anatomical, breathable, textile and expanded polymeric material	Thickness	3,5±0,5 mm	N/A	5.7.1
	pH value	N/A	Not detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm ²	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	No damage	Dry: no holes till 25600 cycles; humid: no holes till 12800 cycles	5.7.4.2
	Chromium VI	N/A	Not detectable	5.7.5

Sole					
Component	Description	Value	Norm requirements	EN 20345	
PU MONODENSITY sole	Sole thickness without profiles	10 mm	≥ 4 mm	5.8.1.1	
	Profile height	4 mm	≥ 2,5mm	5.8.1.3	
	Tear resistance	6,3 kN/m	≥ 5 kN/m	5.8.2	
	Abrasion resistance	<ul style="list-style-type: none"> Relative volume loss 	165 mm ³	≤ 250 mm ³	5.8.3
	Flexionresistance	<ul style="list-style-type: none"> Notches increaseafter 30.000 cycles 	3 mm	≤ 4 mm	5.8.4
	Hydrolysis	<ul style="list-style-type: none"> Notches increase after 150.00 cycles 	4,5 mm	≤ 6 mm	5.8.5
	Tread-midsole detachment	N/A	≥ 4 N/mm; (*) ≥ 3 N/mm with sole ripping	5.8.6	
	(HRO) contact heat resistance (300°C)	N/A	No damage (melting, breaking)	6.4.1	
	(FO) fue lresistance (volume variations)	0,5 %	≤ 12%	6.4.2	

Date: 02/04/2013

Copy in accordance with the Italian sheet